

Our Ref: LAS/RM

04 July 2024

Report 424000**Page 1 of 3**

Camira Transport Fabrics Limited
Meltham Mills
Meltham
West Yorkshire
HD9 4AY

Contact: Luke Russell

| | | |
|-------------------|---|-----------------|
| DATE RECEIVED | : | 28 JUNE 2024 |
| DATE TESTED | : | 04 JULY 2024 |
| QUALITY REFERENCE | : | SUPER TRIM PLUS |
| COLOUR / DESIGN | : | ANTHRACITE |
| STYLE NUMBER | : | 244100300621 |
| ORDER NUMBER | : | 81A28063 |

REQUEST: FMVSS 302:1991 Flammability of interior materials in motor vehicles

RESULT: The sample submitted meets the requirements of FMVSS 302:1991



R. MASKILL
FLAMMABILITY TECHNOLOGIST



L. SMITH
QUALITY COORDINATOR

This report shall not be reproduced except in full without written approval of Eurofins MTS Consumer Product Testing UK Limited. In all circumstances results of tests are implied as referring only to the sample supplied and should not be construed or interpreted on any other basis. The comments given in the report are for guidance only and are not a part of the results. Where specified in a test method preconditioning in accordance with ISO 139 is not carried out as samples are exposed to the conditioning atmosphere specified within ISO 139 for a minimum of 16 hours prior to test.



1428

Our Ref: LAS/RM

04 July 2024

Report 424000**Page 2 of 3****FIRE TESTS ACCORDING TO FMVSS 302:1991**
Flammability of interior materials in motor vehicles**Procedure**

Five specimens were cut to the below dimensions and tested as a single material in accordance with the above standard using a butane flame measuring 38mm in height.

Specimen Length: 356mm
Specimen Width: 102mm
Specimen Thickness: <13mm

Requirements

- : The material shall not burn nor transmit a flame front across its surface at a rate of more than 102 mm per minute.
- : If a material stops burning before 60 seconds and has not burned more than 51mm from the start point, then it shall meet the burn rate requirements.

Results

The following test results relate only to the ignitability of the combination of materials under the particular conditions of test; they are not intended as a means of assessing the full potential fire hazard of the materials in use.

They also only relate to the materials tested. They do not guarantee to represent the performance of production materials.

The specimens were tested in the length direction.

| <i>Parameters</i> | <i>1</i> | <i>2</i> | <i>3</i> | <i>4</i> | <i>5</i> | <i>Mean</i> |
|------------------------|----------|----------|----------|----------|----------|-------------|
| Burning Time [sec] | DNI | DNI | DNI | DNI | DNI | / |
| Burning Distance [sec] | / | / | / | / | / | / |
| Burn Rate [mm/min] | / | / | / | / | / | / |

DNI: Did Not Ignite, SE: Self-Extinguished before start point.

Comments

The sample submitted meets the requirements of FMVSS 302:1991

Our Ref: LAS/RM

04 July 2024

Report 424000**Page 3 of 3****Decision rules**

The decision rule applicable to statements of conformity relating to the test(s) carried out is simple acceptance based on the measured test results not falling within a range either side of a specified limit that is equal to the uncertainty of measurement for the parameter measured (based on 95% confidence levels). In all other regards, the decision rule is based on simple acceptance predicated upon the conditions of testing falling within the criteria for test set out in the test method with a conformance probability of 95%. The risk of false accept or false reject is therefore not greater than 2.5%.

Uncertainty of measurement:

| | |
|------------|-------------|
| Timings | $\pm 1.0s$ |
| Dimensions | $\pm 0.5mm$ |

